



CERTIFICATE OF QUALITY

EcoSure® Type GP Cement

NZS3122:2009 (Bulk & Bag Dispatch)



Issued to: National Sales Manager

Test Report No: 25#79

info@goldenbay.co.nz

Code	Week Ending / Voyage	Specific Surface Area	Normal Consistency	Initial Set	Final Set	Sound- ness	Compressive Strength								Free Lime	Sodium Equivalent (NaEq)	Sulphur Trioxide (SO ₃)
							ISOCEN			Concrete							
							3 days	7 days	28 days	Slump	3 days	7 days	28 days				
Mean		380	29.5	163	3:57	1	35.6	48.3	64.5	87	30.6	40.8	51.9	1.5	0.55	2.31	
Standard Deviation		14	0.5	11	0:12	0.4	1.1	1.3	1.3	9	3.1	3.8	4.3	0.2	0.01	0.04	
Min		360	28.5	135	3:30	0	33.3	45.9	61.5	80	25.0	32.5	44.5	1.1	0.52	2.23	
Max		405	29.8	180	4:30	2	37.3	51.1	66.8	110	34.0	45.5	57.0	2.1	0.58	2.44	
NZS 3122:2009 Requirements				45 min	6:00 max	5 max		35.0 min	45.0 min						0.6 max	3.5 max	
Units		m ² /kg	%	minutes	hrs:mins	mm	MPa	MPa	MPa	mm	MPa	MPa	MPa	%	%	%	
250605-917-GP	05/06/25	385	28.8	150	4:30	1	36.4							1.4	0.54	2.23	
250601-735-GP	01/06/25	395	28.5	150	4:00	1	35.5			80	35.0			1.4	0.54	2.32	
250528-481-GP	28/05/25	380	28.5	165	4:00	1	34.2	47.7		90	27.5	37.0		1.5	0.54	2.33	
250524-179-GP	24/05/25	400	28.5	165	3:45	1	34.4	47.2						1.1	0.55	2.34	
250520-086-GP	20/05/25	390	28.5	180	4:00	0	35.3	48.8		90	28.5	37.0		1.6	0.55	2.25	
250516-090-GP	16/05/25	405	28.7	165	3:45	1	34.9	47.5						1.6	0.54	2.32	
250512-934-GP	12/05/25	405	29.7	180	4:15	1	34.6	45.9		80	33.0	42.0		1.5	0.53	2.32	
250510-936-GP	10/05/25	390	29.8	180	4:00	1	36.3	49.3						1.5	0.55	2.28	
250506-807-GP	06/05/25	365	29.8	165	4:00	1	34.9	49.2	64.6					1.5	0.54	2.30	
250504-805-GP	04/05/25	400	29.7	165	4:00	2	34.7	47.5	64.4	110	25.0	32.5	44.5	2.1	0.54	2.36	
250501-528-GP	01/05/25	375	29.8	165	3:45	1	33.3	46.7	63.5					2.0	0.55	2.25	
250427-406-GP	27/04/25	380	29.8	165	3:45	1	33.7	46.4	61.5	90	28.5	39.0	56.0	1.9	0.56	2.25	
250423-116-GP	23/04/25	390	29.8	165	4:00	1	36.4	49.1	64.3	80	34.0	45.0	57.0	1.4	0.56	2.32	
250419-958-GP	19/04/25	380	29.7	150	4:00	1	36.8	49.2	65.0	90	32.5	45.5	53.5	1.6	0.58	2.30	
250407-515-GP	07/04/25	370	29.7	165	4:00	1	35.7	47.4	65.2	80	30.5	41.5	49.0	1.6	0.56	2.29	
250404-340-GP	04/04/25	375	29.7	165	3:45	2	37.1	49.9	64.6					1.5	0.57	2.35	
250331-214-GP	31/03/25	380	29.8	165	4:00	1	36.7	48.5	62.8	80	34.0	43.5	56.5	1.5	0.56	2.31	
250327-922-GP	27/03/25	365	29.7	180	4:15	1	36.2	49.5	66.8					1.3	0.57	2.31	
250323-924-GP	23/03/25	385	29.8	165	4:00	1	36.0	49.5	64.6	100	29.0	41.0	49.0	1.3	0.57	2.33	
250319-584-GP	19/03/25	370	29.8	165	3:45	0	37.3	48.7	65.3					1.3	0.56	2.44	
250316-582-GP	16/03/25	360	29.7	165	4:15	1	36.3	48.4	63.7	80	30.0	43.5	50.5	1.5	0.55	2.30	
250312-330-GP	12/03/25	360	29.8	135	3:30	1	35.9	51.1	66.6					1.3	0.54	2.37	
250308-321-GP	08/03/25	365	29.7	150	3:45	1	36.4	48.7	64.8	90	33.5	43.0	53.5	1.3	0.54	2.36	
250305-953-GP	05/03/25	365	29.5	150	4:00	2	35.0	48.9	64.9	80	26.0	36.5	46.5	1.3	0.54	2.31	
250301-730-GP	01/03/25	360	29.7	165	4:00	1	36.0	46.4	63.1	80	32.0	44.0	55.0	1.1	0.52	2.32	

The above samples were tested as received in accordance with the current terms of accreditation and methods stated in NZS 3122:2009 with the exception of:
Chemical composition to ASTM C114-23

All concrete testing conducted in accordance with NZS 3112:1986.

This Report must not be reproduced except in full

V. Lane

Vincent Lane
Works Chemist



Portland Works, Portland, Whangarei 0178


Date issued: 13/06/2025

Page 1 of 3



EcoSure® Type GP Cement

Compressive Strength ISO-CEN Mortar (Bulk Dispatch)





EcoSure® Type GP Cement

Compressive Strength Concrete (Bulk Dispatch)

